



MOSCONI s.r.l.



TECHNICAL DATA SHEET

INSULATING AGGREGATE 6-15

Max. service temperature °C	1000
Bulk density Kg/m ³	260
Chemical Analysis	SiO ₂ % Al ₂ O ₃ % TiO ₂ % Fe ₂ O ₃ %	65,0 16,0 0,5 4,0
Thermal conductivity BS 1902 Section 5.5 1991	200°C W/m ² K 400°C W/m ² K 600°C W/m ² K	0,14 0,17 0,19
Grain size % by weight passing ISO sieves	> 15 mm % 10-15 mm % 6-10 mm % < 6 mm %	2 18 70 10
Packing	Bags (50 dm ³) kg big bags (1,0 m ³) kg	13 260

Issued: January 2016

The above-mentioned data, resulting from our testings, are given as an indication of typical values.
No guarantee can be granted regarding their absolute values or working performances.